

Marked up Version of the Claims

1. CANCELLED
2. CANCELLED
3. CANCELLED
4. CANCELLED
5. CANCELLED
6. CANCELLED
7. CANCELLED
8. CANCELLED
9. CANCELLED
10. (Previously Presented) An element for the casting of a liquid metal, comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal, wherein at least a part of the element inner surface is coated with an insulating coating comprising insulating hollow microspheres, preferably in an amount comprised between 5 and 40 weight % and forming, at the metal liquid contact, a gas impermeable layer.
11. (Currently Amended) A casting element according to claim [1]10, wherein the coating comprises 20 to 80 weight % of a ceramic matrix.
12. (Previously Presented) A casting element according to claim 11, wherein the ceramic matrix comprises silica or alumina.
13. (Currently Amended) A casting element according to claim [2]12, wherein the ceramic matrix comprises vitreous grains.
14. (Previously Presented) A casting element according to claim 13, wherein the vitreous grains comprise atomized silica.

15. (Currently Amended) A casting element according to claim [1]10, wherein the thickness of the coating is between 1 and 10 mm.
16. (Currently Amended) A casting element according to claim [1]10, wherein the impermeable layer and the refractory material are interpenetrated.
17. (Currently Amended) A casting element according to claim [1]10, wherein the base body is constituted from a carbon bonded material.
18. (Currently Amended) A casting element according to claim [1]10, wherein the casting element is a pouring shroud.
19. (Currently Amended) A casting element according to claim [1]10, wherein at least a part of the external surface is coated with an insulating coating comprising insulating microspheres.
20. (Previously Presented) A casting element according to claim 19, wherein the insulating microspheres comprise between 5 and 40 weight % of the insulating coating.
21. (Previously Presented) A method of coating a casting element comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal, comprising the steps of preparing a slip comprising insulating hollow microspheres, drying the slip at room temperature, preferably for at least two hours, and forming a gas impermeable layer from the dried slip by contacting the dried slip with liquid metal.